

WELLINGTON—continued.

- Dacrydium cupressinum*, Native name *Rimu*.
Attains a diameter of 4 feet; wood valuable for building purposes; heart-wood of old trees adapted for cabinet work. Locality, Wellington, N. Island.
- Myoporum laetum*, Native name *Ngaio*.
Attains a diameter of 12 to 18 inches; an ornamental tree. Locality, Wellington, N. Island.
- Carpodetus serratus*, Native name, *Piripiriwhata*.
Attains a diameter of 12 to 18 inches; an ornamental tree. Locality, Wellington, N. Island.
- Aristotelia racemosa*, Native name *Makomako*.
Attains a diameter of 8 to 12 inches; an ornamental tree. Locality, Wellington, N. Island.
- Melicytus ramiflorus*, Native name *Mahoe*.
Attains a diameter of 2 feet; an ornamental tree. Locality, Wellington, N. Island.
- Olearia traversii*, Native name *Ake*.
Attains a diameter of 12 to 18 inches; wood adapted for cabinet work, free from the attack of insects. Locality, Chatham Islands.
- Senecio huntii*.
Attains a diameter of 6 to 8 inches; ornamental shrub. Locality, Chatham Islands.
- Hedera crassifolia*, Native name *Oho*.
Attains a diameter of 6 to 8 inches; ornamental shrub. Locality, Chatham Islands.
- Myrsine chathamica*, Native name *Matipo*.
Attains a diameter of 1 to 2 feet; ornamental shrub tree. Locality, Chatham Islands.
- Korokia buddleoides*, Native name *Korokiataranga*.
Attains a diameter of 12 to 15 inches; an ornamental shrub. Locality, Chatham Islands.
- Veronica forsteri*, Native name *Koromiko*.
Attains a diameter of 6 to 8 inches; ornamental shrub. Locality, Chatham Islands.
- Coprosma propinqua*, Native name *Karamu*.
Attains a diameter of 6 to 8 inches.
- Dracophyllum urvilleanum*.
Attains a diameter of 6 to 12 inches; adapted for cabinet work. Locality, Chatham Islands.

SOUTH ISLAND—

- Melicytus ramiflorus* (Hini-Hini, Whitewood or Mahoe).
A small tree; wood white, ornamental. Locality, Pigeon Bay, Banks' Peninsula.
- Pittosporum tenuifolium* (Black Mapau or Tarata).
A small tree; wood white, takes a fine polish. Locality, Pigeon Bay, Banks' Peninsula.
- Pittosporum eugenioides* (White Mapau).
Larger than the preceding; wood soft, white, very ornamental. Locality, Pigeon Bay, Banks' Peninsula.
- Pittosporum* (new species).
A small tree, one foot diameter; wood white, rather hard, ornamental. Locality, Otira, Westland.
- Plagianthus betulinus* (Ribbonwood).
A large ornamental quick-growing tree, with very fibrous bark, which might be used for making paper; wood soft, light. Locality, Pigeon Bay.
- Plagianthus lyellii* (Alpine Ribbonwood).
A small tree, with similar properties to the common Ribbonwood. Locality, Arthur's Pass, Westland.
- Elæocarpus hookerianus* (Pokako).
A very large tree, with light soft wood, which is used for cabinet work and sometimes for boats. The bark yields a fine purple dye. Locality, Pigeon Bay.
- Elæocarpus dentatus*, var. (Hinau).
A large tree something like the last, but the wood is lighter and softer. Locality, Otira Junction, Westland.
- Aristotelia racemosa* var. (Mako).
A small tree, with light beautifully marked wood, veneers, &c. Locality, Otira Junction, Westland.
- Pennantia corymbosa* (Kaikomako or Ribbonwood).
A small tree, wood very light, white. Locality, Pigeon Bay, Banks' Peninsula.
- Discaria toumatou* (Wild Irishman).
A small spiny tree, with a fine-grained hard wood, which might be used for veneers. Locality, Bruce's Creek, Waimakariri District, Canterbury.
- Alectryon excelsum* (Titoki).
A strong and valuable though small timber; used for wheels, coach-building, &c., exceedingly durable. Locality, Pigeon Bay, Banks' Peninsula.
- Sophora tetraptera* (Kowhai, Goai).
A very durable and valuable timber, stands well in water; used for cabinet work, axe-handles, and general purposes. Locality, Little River, Canterbury.
- Carpodetus serratus* (Oak, White Matipo).
A small ornamental tree, wood white and tough; used for axe-handles. Locality, Pigeon Bay.

SOUTH ISLAND—continued.

- Weinmannia racemosa* (Karmai, Towhai).
A tall fine tree, producing a very heavy, hard, and durable wood, which will probably be used for various purposes. Locality, Otira Junction.
- Leptospermum scoparium* (Manuka).
A small tree with red wood, which is stronger than any other native timber; used for marine work, &c. Locality, Little River, Canterbury.
- Metrosideros lucida* (Rata).
A strong and very durable timber, will be much used for ship-building and cabinet work. Locality, Arthur's Pass (from small tree).
- Fuchsia excorticata* (Konini, Fuchsia).
A fine tree, with white wood mottled with purple; used for cabinet work. The wood yields a purple dye. Locality, Pigeon Bay, Banks' Peninsula.
- Fuchsia excorticata*.
Locality, Little River, Canterbury.
- Panax crassifolium* (Lancewood).
A large tree, wood tough, light coloured, and durable; might be used in cabinet work. Locality, Pigeon Bay.
- Panax crassifolium*, varieties (Horocka, Lancewood).
A large tree, similar to last. Locality, Otira Junction.
- Panax colensoi* (Ivy tree).
A small ornamental tree, wood soft and tough, yields a yellow resin. Locality, Otira Junction.
- Panax edgerleyi* (Rakawa).
A small tree, with similar properties to the last. Locality, Otira Junction.
- Panax crassifolium* (Lancewood).
Locality, Little River, Canterbury.
- Grisebina littoralis* (Broadleaf).
A large tree, with hard red hearted timber, which is very durable. Locality, Little River.
- Coprosma linearifolia* (Mingimingi).
A small tree, wood yellow, curiously marked; used for veneers and axe handles. Locality, Little River.
- Olearia forsteri* (Ake-ake).
A small tree about 12 inches diameter, wood dark, heavy, very hard and durable; used for cabinet work. Locality, Little River, Canterbury.
- Olearia ilicifolia*, Holly (Ake-ake).
A small tree, with yellowish wood, not so good as the last. Locality, Arthur's Pass.
- Dracophyllum traversii* (Nei-Nei).
A short, stout, slow-growing tree, of very curious appearance, wood light coloured, beautifully marked, tough, and probably of considerable value. Locality, Arthur's Pass.
- Myrsine urvillei* (Red Mapau).
A small slender tree, wood very beautiful; used for veneers. Locality, Pigeon Bay.
- Myoporum laetum* (Ngaio).
A small ornamental tree, wood light, white, and tough; used for gun stocks. Pigeon Bay, Canterbury.
- Fagus fusca* (large-leaved Birch).
A fine tree, 100 feet high, 3-16 feet diameter, wood red, durable, splits freely; used for all building purposes. Locality, Otira Junction.
- Epicarpurus microphyllus* (Milk tree).
A tall slender tree, exuding a milky sap, wood white, very brittle. Locality, Little River.
- Epicarpurus microphyllus* (Milk tree).
Similar to the last. Locality, Pigeon Bay.
- Libocedrus bidwilli* (Kawaka Cedar).
A small beautiful evergreen tree, wood red, soft hearted; used for cabinet work. Locality, Arthur's Pass.
- Podocarpus ferruginea* (Miro).
Wood used for various purposes, not very durable. Locality, Little River.
- Podocarpus nivalis* (Mountain Totara).
A fine tree, 80 feet high, 3 feet diameter, somewhat like Totara (*Podocarpus totara*), but with smoother bark; wood light red colour, easily worked, and durable; used for houses and bridges, telegraph poles, &c. Locality, Otira Junction.
- Dacrydium cupressinum* (*Rimu*, Red pine).
Locality, Otira Junction.
- Dacrydium colensoi* (Yellow Pine).
A small tree; wood white or yellow, light and soft. Locality, Otira Junction.
- Phyllocladus alpinus* (Toa-toa).
A small alpine pine; wood heavy and durable. Locality, Arthur's Pass, Westland.
- Pennantia corymbosa* (Kaiko-mako).
Locality, Little River.